



SCREEN PROCESS STENCIL MATERIALS SALES PROGRAM AND PRODUCT DESCRIPTION

FOTECHEM FRAME ADHESIVES

Date: 11/11 Page: 8

Code <small>3rd letter for size</small>	Prod. NO.		Use	Condition	Colour	Description	Sizes available (kg/lt)				
											Specials
LC .	2320	RED	Frame adhesive	liquid	red	totally solvent resistant; to be mixed with 2325 5 : 1 by weight	6 x 0,9 kg	6 x 4,5 kg			1 x 125 kg
LD .	2325	2 components	Hardener for 2320 and 2320 HV	liquid	red	catalyst; mix 1 to 5 by weight	6 x 0,18kg	6 x 0,9 kg		1 x 25 kg	
	2320HV	RED	Frame adhesive	liquid	red	totally solvent resistant; to be mixed with 2325 5 : 1 by weight	6 x 0,9 kg	6 x 4,5 kg			1 x 125 kg
LE .	2330	CLEAR	Frame adhesive	liquid	clear	totally solvent resistant; to be mixed with 2335 5 : 1 by weight	6 x 0,9 kg	6 x 4,5 kg			1 x 125 kg
LF .	2335	2 components	Hardener for 2330	liquid	clear	catalyst; mix 1 to 5 by weight	6 x 0,18kg	6 x 0,9 kg		1 x 25 kg	
LG .	2350	GREEN	Frame adhesive	liquid	blue	totally solvent resistant; to be mixed with 2355 5 : 1 by weight	6 x 0,9 kg	6 x 4,5 kg			1 x 125 kg
LH .	2355	2 components	Hardener for 2350	liquid	yellow	catalyst; mix 1 to 5 by weight	6 x 0,18kg	6 x 0,9 kg		1 x 25 kg	
LS .	2327		Thinner for frame adhesives	liquid	clear	thinner can be used for all FOTECO frame adhesives EXCEPT 2340	6 x 1 lt	6 x 5 lt			
LK .	2340	1 component	Frame adhesive	liquid	trans- parent	rapid drying; reduced solvent resistance		6 x 5,0 kg		1 x 23 kg	1 x 180 kg

Hints:

2320 / 2325 mixture has a low viscosity

2330 / 2335 and 2350 / 2355 and 2320 HV / 2325 mixtures have a higher viscosity, a better humidity resistance and a slightly shorter retention/drying time