



Fotec AG

Phone:

e-mail:

Eigenheimstr. 22 CH-8700 Küsnacht

P.O.Box 1123 Switzerland

+41 44 913 30 00 Fax: +41 44 910 45 25

info@fotec.ch

www.fotec.ch

TECHNICAL INFORMATION

Küsnacht, March 2000

FOTECOAT 1970

Sensitising with the new FOTECO DIR-AD system

Economic, fool-proof, all purpose screen emulsion

1. Description

- Dual-cure, photopolymer screen emulsion
- Ideal for most ink systems
- Can be sensitized by direct addition of the sensitizer powder
- The sensitizer is supplied in air-tight, insulated sachets for long shelf-life
- Can be post-exposed to improve the through-curing.
- Blue colour with high contrast
- Excellent adhesion to all meshes
- After sensitizing 33% solids content
- The exposure time is short
- Environmentally safe

2. Coating

- Ideal viscosity for coating on most mesh numbers
- Coatable wet in wet or with intermediate drying cycle
- Can be used for manual- or hand-coating

3. Stencil quality

- Resolution on polyester monofilament 120-34 yellow: 50 μ ; excellent mesh bridging.
- To lower the Rz-value 1-2 additional coats can be added after an intermediate drying cycle. After this the stencil should be dried with print-side upwards.

4. Storing

- | | |
|--|--------------|
| – Unsensitized | Up to 1 year |
| – Sensitized at 20°C | 3 - 4 weeks |
| – Shelf-life for coated screens, complete darkness, at 20°C and 60% RF | 2 months |

5. Exposure

- Dry the stencil completely before exposure and never use heat over 40°C.
- 5KW metal halide lamp with photopolymer bulb at 100 cm distance and after 100 operating hours:
 - Polyester monofilament: 120-34 Y: 2P/3S = 11 μ = 60 seconds
 - Polyester monofilament: 120-34 Y: 1P/2S = 7 μ = 50 seconds
 - Polyester monofilament: 43-80 W: 1P/1S = 12 μ = 100 seconds

6. Removal

- Standard stencil decoating chemicals can be used such as FOTECHEM 2044 (powder), 2005 (paste), 2042 (concentrated liquid), 2004 (liquid ready-to-use).
- The decoating chemical should never dry on the stencil.
- Whenever possible degrease before the decoating; this facilitates decoating and helps to prevent ghost-pictures.
- Important: a fully exposed stencil, with complete through-curing, or a post-exposure, renders the stencil removal faster and easier.
- To remove diazo stains use FOTECHEM 2125.
- To eliminate haze, residues, ghost pictures: FOTECHEM 2080 paste together with FOTECHEM 2085 Regenerator Liquid is recommended.

FOTEC AG

These Technical Informations are published without warranty. The results shown in these Technical Informations are based on laboratory testing. The supplier declines any responsibility for incorrect use of these products which are manufactured and sold for industrial use only.